

## Flexcon OptiFlex® PP 230 H White TC-332™ A-32 Special 50K-8

Primary and Secondary Labeling White Polypropylene FLX022786

#### **Benefits**

• Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping

### **Features**

- 2.3 mil white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Excellent surface smoothness allows for optimum ink laydown
- Film conformability for rigid containers provides maximum label and graphic coverage
- · Permanent pressure-sensitive acrylic adhesive bonds well to glass, low- and high-surface energy plastics without lifting, tunneling or flagging
- Adhesive offers excellent tack, clarity and wet-out characteristics
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting

#### **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Film	2.3 +/- 10 %	58
Adhesive	0.6-0.7 +/- 0.1	15-18 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon OptiFlex® PP 230 H White TC-332™ A-32 Special 50K-8

Primary and Secondary Labeling White Polypropylene FLX022786

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	41	451
Acrylic	50	550
Glass	45	495
Polypropylene	3	33

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear	25	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack	760	ASTM D 2979
Additional Information		
Service Temperature	-20°F to 212°F (-29°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

### **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.