

CompuCal® Excel[™] 20440 MTC-722 MATTE TOPCOAT 2 MIL CLEAR PET WITH HIGH PERF ADH ROLL FORM LINER

Durable Goods and Equipment Labeling - Matte Topcoated Clear Polyester - Thermal Transfer Printable FLX000282

Benefits

- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- CSA accepted under CSA File No. 99214

Features

- 2.0 mil matte topcoated clear polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Matte topcoated 2.0 mil white polyester provides consistent surface smoothness, excellent dimensional stability, and endurance to varying temperatures
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); narrow-format UV inkjet; UV letter press; and UV offset
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate
 and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.1 +/- 10 %	53
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



CompuCal® Excel™ 20440 MTC-722 MATTE TOPCOAT 2 MIL CLEAR PET WITH HIGH PERF ADH ROLL FORM LINER

Durable Goods and Equipment Labeling - Matte Topcoated Clear Polyester - Thermal Transfer Printable FLX000282

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Acrylic	77	847
Glass	68	748
Polypropylene	15	165

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method	
Expected Shear	30	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)	
Tack	1030	ASTM D 2979	
Additional Information			
Service Temperature	-40°F to 302°F (-40°C to 150°C)	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% r humidity	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.