

CompuCal® Excel™ 21440 MTC-722 Matte Topcaot 2 MIL White PET with High Performance Adhesive Roll Form Liner

Durable Goods and Equipment Labeling - Matte Topcoated White Polyester - Thermal Transfer Printable FLX000284

Benefits

- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- Full color static and variable printing in one pass together with UL PGJI2 recognition when printed on a Jetrion 4000 series UV Inkjet System
- CSA accepted under CSA File No. 99214

Features

- 2.0 mil matte topcoated white polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Matte topcoated film designed for cross-technology printability via narrow-format UV inkjet, impact, laser, electron beam, wax, resin and wax/resin
 thermal transfer (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions
- Topcoat provides excellent resistance to chemicals, moisture, smudging and scratching
- Unique matte topcoat allows for greater than four times as many die revolutions before retooling compared with competing label materials
- Permanent pressure-sensitive acrylic adhesive bonds well to low- and high-surface energy plastics, metal and paint
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.1 +/- 10 %	53
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3
Liner	Liner: 3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



CompuCal® Excel™ 21440 MTC-722 Matte Topcaot 2 MIL White PET with High Performance Adhesive Roll Form Liner

Durable Goods and Equipment Labeling - Matte Topcoated White Polyester - Thermal Transfer Printable FI X000284

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Acrylic	77	847
Glass	68	748
Polypropylene	15	165

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear	30	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	1030	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.