



Flexcon® DPM® FWS White Vinyl Hi-Perf Adhesive Sheet Liner

Durable Goods and Equipment Labeling Flexible White Vinyl - Sheet Form

FLX000308

Benefits

- Ideal for sheet-form converting
- Adhesive bonds well to base film substrates

Features

- CSA Acceptance, L- Adhesives, UL Recognized
- 3.5 mil double-faced flexible white vinyl
- Print-receptive 4.0 mil white flexible vinyl provides consistent surface smoothness, excellent dimensional stability, and conformability
- Printable via thermal transfer, UV and solvent screen, UV, solvent & water flexo, and narrow-format UV inkjet
- In most cases, corona treatment is not required
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Backed on both sides with a 90 lb. polycoated layflat release liner

Additional Details

- Order custom widths without purchasing a whole master through Flexcon® [FlexChoice™](#) for Durables

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	3.5 +/- 10%	89
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® DPM® FWS White Vinyl Hi-Perf Adhesive Sheet Liner

Durable Goods and Equipment Labeling Flexible White Vinyl - Sheet Form

FLX000308

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	101	1111
Acrylic	69	759
Glass	64	704
Polypropylene	24	264

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear	15	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	750	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.