



DPM® PCRTS 2 MIL Printable Clear PET High Performance Adhesive for Rough/ Textured Surfaces Roll Liner

Durable Goods and Equipment Labeling Clear Polyester for Rough Textured Surfaces - Roll Form
FLX000312

Benefits

- Ideal for roll to roll converting
- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214

Features

- 2.0 mil clear polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Print-receptive surface is compatible with most conventional and UV ink systems (we recommend evaluating the intended ink system for compatibility with the product under the application conditions)
- Acrylic adhesive offers high initial tack, high shear, and high ultimate bond to a wide variety of rough textured surfaces, including low-surface energy plastics and painted metal
- 50 lb. bleached kraft release liner offers good diecutability

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10 %	51
Adhesive	1.9-2.1 +/- 0.1	48-53 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	104	1144
Acrylic	112	1232
Glass	118	1298
Polypropylene	22	242

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	100	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	1520	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.