

## Flexcon® ThermlFilm® NexGen™ 24110

2.0 Mil Gloss Topcoated Satin Silver Polyester, Permanent Adhesive, Roll-Form Liner FLX054105

## **Benefits**

- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- cUL recognized under UL File No. PGJI8.MH16635 Printing Materials Certified for Canada Component under CAN/CSA standard C22.2, No. 0.15
- CSA accepted under CSA File No. 99214

## **Features**

- 2.0 mil gloss topcoated satin silver polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Topcoat is more universally printable than other thermal transfer printable products
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate
  and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- 50 lb. bleached kraft release liner made from up to 30% post-consumer waste, ideal for roll form converting
- Liner is suitable for optical sensing on most thermal transfer printers

## **Additional Details**

## **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10%	51
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® ThermlFilm® NexGen™ 24110

2.0 Mil Gloss Topcoated Satin Silver Polyester, Permanent Adhesive, Roll-Form Liner FLX054105

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	68	748
Acrylic	71	781
Glass	65	715
Polypropylene	24	264

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear		
Tack	800	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	2

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.