



# Flexcon® ThermoFilm® NexGen™ 20120

2.0 Mil Gloss Topcoated Clear Polyester, Permanent Adhesive, Roll-Form Liner  
FLX054108

## Benefits

- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- UL recognized under UL 969 - UL File No. PGJ12.MH16635 Printing Materials - Component
- cUL recognized under UL File No. PGJ18.MH16635 - Printing Materials Certified for Canada - Component - under CAN/CSA standard C22.2, No. 0.15
- CSA accepted under CSA File No. 99214
- Order custom widths without purchasing a whole master through Flexcon® FlexChoice™ for Durables

## Features

- 2.0 mil clear gloss topcoated polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- 50 lb. bleached kraft release liner made from up to 30% post-consumer waste, ideal for roll form converting
- Liner is suitable for optical sensing on most thermal transfer printers
- 

## Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10%	51
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Acrylic	77	847
Glass	68	748
Polypropylene	15	165

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	30	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	1030	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.