



Benefits

- Excellent adhesion to a wide variety of smooth surfaces
- Resistant to cold flow and ooze

Features

- 0.5 mil double-faced clear polyester carrier film
- Excellent adhesion to a wide variety of smooth surfaces, including painted and unpainted metals and high- and low-surface energy plastics
- Adhesive has high peel and high shear characteristics resistant to cold flow and ooze
- Suitable for a wide range of temperature conditions
- Backed with an 80 lb. double-faced release liner
- Ideal for roll-form and roll-to-sheet converting

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	0.5 +/- 10%	13
Adhesive	1.0-1.1 +/- 0.1 (3)	25-28
Liner	5.6 +/- 10%	142

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	63	693
Glass	45	495
Polypropylene	13	143
Stainless Steel	50	550

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear		
Tack	780	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.