

Flexcon® OptiFlex® Reseal™ 21133

Resealable Closure White Polypropylene: 2.3 Mil White BOPP TC, Resealable Adhesive, TracRite™ 120 FLX064717

Benefits

Adhesive complies with 21 CFR 175.105 for indirect food contact

Features

- Topcoated 2.3 mil hard white polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity and product contents
- Film opacity is ideal for achieving high-image graphics
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, narrow-format UV inkjet, roll-form dry toner, UV rotary screen, UV letterpress and hot stamping
- Resealable pressure-sensitive acrylic adhesive bonds well to low- and high-surface energy laminated flexible packaging substrates with clean, quiet, and consistent reclosure
- Adhesive offers excellent clarity and wet out characteristics
- Polyester release liner for excellent on-press performance for tight-registration graphics and contains up to 60% post lidustrial recycled content, provides good diecutting base and allows for high-speed dispensing

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Film | 2.3 +/- 10 % | 56 |
| Adhesive | 0.7-0.8 +/- 0.1 | 18-20 +/- 3 |
| Liner | 1.2 +/- 10 % | 30 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® OptiFlex® Reseal™ 21133

Resealable Closure White Polypropylene: 2.3 Mil White BOPP TC, Resealable Adhesive, TracRite™ 120 FLX064717

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 16 | 176 |
| Acrylic | 22 | 242 |
| Glass | 15 | 165 |
| Polypropylene | 13 | 143 |

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear | Room Temp (hours): 100+ | ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load |
| Tack | 440 | ASTM D 2979 |
| Additional Information | | |
| Service Temperature | -20°F to 212°F (-29°C to 100°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.