

Flexcon® OptiFlex® Reseal™ 21133

Topcoated 2.3 Mil White BOPP, High-Performance Resealable Adhesive, TracRite™ 120 FLX064717

Benefits

- Excellent surface smoothness allows for optimum ink laydown
- Adhesive complies with 21 CFR 175.105 for indirect food contact
- Order custom widths without purchasing a whole master through FlexCon® FlexChoice™ for Packaging

Features

- Topcoated 2.3 mil hard white polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity and product contents
- Film opacity is ideal for achieving high-image graphics
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks, and hot stamping
- Resealable pressure-sensitive acrylic adhesive bonds well to low- and high-surface energy laminated flexible packaging substrates with clean, quiet, and consistent reclosure
- Adhesive offers excellent clarity and wet out characteristics
- Polyester release liner for excellent on-press performance for tight-registration graphics & contains up to 60% post industrial recycled content

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.3 +/- 10 %	56
Adhesive	0.7-0.8 +/- 0.1	18-20 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® OptiFlex® Reseal™ 21133

Topcoated 2.3 Mil White BOPP, High-Performance Resealable Adhesive, TracRite™ 120 FLX064717

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	16	176
Acrylic	22	242
Glass	15	165
Polypropylene	13	143

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method	
Expected Shear	Room Temp (hours): 100+	ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load	
Tack	440	ASTM D 2979	
Expected Exterior Life	Indoor use only		
Additional Information			
Service Temperature	-20°F to 212°F (-29°C to 100°C)	-20°F to 212°F (-29°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	е	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.