

# Flexcon® FlexMark® UVOL 500 Clear Velvet V-344 150 Poly H-9

Durable Goods and Equipment Labeling Clear Velvet UV Resistant Polycarbonate - Overlaminate FLX067807

### **Benefits**

• 5 year outdoor durability

#### **Features**

- 5.0 mil clear velvet overlaminating polycarbonate that protects against damaging UV rays, moisture & scratching
- Permanent pressure-sensitive acrylic adhesive bonds well to printed film
- Backed with an ultra-smooth clear polyester release liner

### **Additional Details**

### **Technical Data**

#### **Physical Properties**

| Thickness (Mils [microns]) | Mils            | Microns     |
|----------------------------|-----------------|-------------|
| Film                       | 5.0 +/- 10 %    | 127         |
| Adhesive                   | 1.4-1.5 +/- 0.1 | 36-38 +/- 3 |
| Liner                      | 1.4 +/- 10 %    | 36          |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



## Flexcon® FlexMark® UVOL 500 Clear Velvet V-344 150 Poly H-9

Durable Goods and Equipment Labeling Clear Velvet UV Resistant Polycarbonate - Overlaminate FLX067807

#### **Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel    | 61            | 671   |
| Acrylic            | 68            | 748   |
| Glass              | 68            | 748   |
| Polypropylene      | 48            | 528   |

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

| Additional Properties           | Value  | Test Method  |
|---------------------------------|--|--|
| Expected Shear                  | 100  | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack                            | 900  | ASTM D 2979  |
| Expected Exterior Life          | 5 Years based on 2000 hours Xenon arc weatherometer exposure |  |
| Additional Information          |  |  |
| Service Temperature             | -40°F to 212°F (-40°C to 100°C)                              |  |
| Minimum Application Temperature | 50°F (10°C)  |  |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% rela humidity        | ative  |

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.