

## Flexcon® NexGen™ CPP344S

Durables Exterior Durable Gloss 4 Mil Topcoated Frosty Clear Polypropylene - High Performance Adhesive Sheet Liner FLX068533

### **Benefits**

- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- cUL recognized under UL File No. PGJI8.MH16635 Printing Materials Certified for Canada Component under CAN/CSA standard C22.2, No. 0.15

#### **Features**

- Gloss topcoated 4.0 mil frosty clear polypropylene (vinyl alternative) provides consistent surface smoothness and excellent dimensional stability
- Printable via resin & wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- 90 lb. moisture stable polycoated release liner is ideal for roll-to-sheet and sheet-form converting on most narrow-format presses
- Five year outdoor durability based on 2500 hrs. Xenon Arc
- All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing. For laser diecutability, please check with your equipment manufacturer.

#### **Additional Details**

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing. For laser diecutability, please check with your equipment manufacturer.

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Film		
Adhesive		
Liner		

Test Method:



# Flexcon® NexGen™ CPP344S

Durables Exterior Durable Gloss 4 Mil Topcoated Frosty Clear Polypropylene - High Performance Adhesive Sheet Liner FLX068533

Adhesion Properties			
Ultimate Peel from	Average Oz/In	(N/m)	
Test Method:			
Additional Properties	Value	Test Method	
Expected Shear			
Tack			
Expected Exterior Life			
Additional Information			
Service Temperature			
Minimum Application Temperature			
Storage Stability			

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.