

## OptiFlex® EcoFocus™ PE 300 F WHITE V-127RE TracRite™ 120

3.0 mil white polyethylene enables recyclability of HDPE containers  ${\sf FLX069058}$ 

### **Benefits**

- · Polyethylene film offers good resistance to a variety of environments, including the shower where moisture and humidity are present
- Adhesive complies with FDA 175.105 for indirect food contact
- APR Critical Guidance Recognition Flexcon's undecorated OptiFlex® EcoFocus® PE 300 F White pressure-sensitive labels, with V-127RE adhesive meet
  or exceed APR's Critical Guidance Protocol for HDPE Colored or Natural Bottles with Resin Additives, Barriers, Labels or Closures, HDPE-CG-01.

#### **Features**

- 3.0 mil white polyethylene offers superior film conformability for maximum label and graphic coverage
- Print-receptive film provides uniform and consistent printability via rotary letterpress, rotary screen, HP Indigo, UV narrow-format inkjet and flexography (in-line corona treatment recommended to enhance print receptivity)
- High-performance adhesive adheres well to HDPE containers
- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing

#### **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Film	3.0 +/- 10%	76
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 5%	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# OptiFlex® EcoFocus™ PE 300 F WHITE V-127RE TracRite™ 120

3.0 mil white polyethylene enables recyclability of HDPE containers FLX069058

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Aluminum	65	715
Glass	54	594
HDPE	28	308

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	10	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack	720	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.