



Benefits

- Adhesive offers excellent tack, clarity and wet out characteristics

Features

- Topcoated 2.0 mil clear polypropylene (BOPP) offers excellent resistance to shrinkage, high-temperature pasteurization, moisture, humidity, and product contents
- Film clarity is ideal for achieving the no-label-look
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Excellent surface smoothness allows for optimum ink laydown
- Backed with Flexcon® TracRite™ 120 polyester release liner for excellent on-press performance for tight registration graphics
- Release liner provides a good diecutting base and allows for high-speed dispensing
- High-performance permanent acrylic adhesive provides a good bond to low- and high-surface energy plastics, and glass for reliable performance in extreme cold temperatures
- Film conformability for rigid containers provides maximum label and graphic coverage
- Topcoat optimizes printability with solvent and water flexo, UV inkjet - (Xeikon Jetrion 4000 series and Domino) Narrow, UV offset, UV Flexo, hot stamping, UV letterpress and UV screen

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10 %	51
Adhesive	0.55-0.65 +/- 0.1	14-17 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	36	396
Acrylic	44	484
Glass	39	429
Polypropylene	6	66
Polyester	43	473

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear	100	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack	480	ASTM D 2979
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.