

## Flexcon® OptiFlex® Polypropylene 230 H W TC-458 V-611 TracRite™ 120

Secondary Labeling White Polypropylene with Removable Adhesive FLX070143

## **Benefits**

- Order custom widths without purchasing a whole master through Flexcon® FlexChoice™ for Packaging
- Adhesive complies with FDA 175.105 for indirect food contact

#### **Features**

- 2.3 mil hard white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film opacity is ideal for achieving high impact graphics
- · Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, UV inkjet (Xeikon Jetrion 4000 series and Domino), UV screen, UV letterpress, and hot stamping
- General-purpose removable adhesive provides minimal adhesion bond over time ensuring clean removability
- Adheres to a wide range of container types
- Backed with Flexcon® TracRite™ 120 polyester release liner for excellent on-press performance for tight registration graphics
- Polyester release liner contains up to 60% Post Industrial Recycled content, provides good diecutting base and allows for high-speed dispensing

## **Additional Details**

## **Technical Data**

#### **Physical Properties**

| Thickness (Mils [microns]) | Mils            | Microns     |
|----------------------------|-----------------|-------------|
| Film                       | 2.0 +/- 10 %    | 51          |
| Adhesive                   | 0.5-0.6 +/- 0.1 | 13-15 +/- 3 |
| Liner                      | 1.2 +/- 10 %    | 30          |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® OptiFlex® Polypropylene 230 H W TC-458 V-611 TracRite™ 120

Secondary Labeling White Polypropylene with Removable Adhesive FLX070143

#### **Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel    | 17            | 187   |
| Glass              | 14            | 154   |
| Polypropylene      | 14            | 154   |
| Polyethylene       | 6             | 66    |
| Aluminum           | 23            | 253   |

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

| Additional Properties           | Value   | Test Method   |
|---------------------------------|---|---|
| Expected Shear                  | 100   | ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load) |
| Tack                            | 290   | ASTM D 2979   |
| Additional Information          |   |   |
| Service Temperature             | -20°F to 212°F (-29°C to 100°C)                           |   |
| Minimum Application Temperature | 40°F (4°C)  |   |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% relative humidity |   |

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.